

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 698 487 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:
28.02.1996 Bulletin 1996/09

(51) Int. Cl.⁶: B32B 27/28, B32B 27/08,
A61J 1/00

(21) Application number: 95910799.6

(86) International application number: PCT/JP95/00410

(22) Date of filing: 10.03.1995

(87) International publication number: WO 95/25010
(21.09.1995 Gazette 1995/40)

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB GRIE IT LI LU MC NL
PT SE

(30) Priority: 15.03.1994 JP 43511/94

(71) Applicant: OTSUKA PHARMACEUTICAL
FACTORY, INC.
Naruto-shi Tokushima 772 (JP)


(72) Inventors:
• INOUE, Fujio
Naruto-shi Tokushima 772 (JP)
• IZUMI, Masamitsu
60, Aza Nanamai
Naruto-shi Tokushima 772 (JP)
• KASHIYAMA, Shigetoshi
101, Aza Nanamai
Naruto-shi Tokushima 772 (JP)

(74) Representative: Schubert, Siegmund, Dipl.-Ing. et al
D-60313 Frankfurt (DE)

(54) CONTAMINATION-PROOF SEALANT FILM AND PRODUCT FABRICATED THEREFROM

(57) A contamination-proof sealant film mainly used in the medical field, which is provided at least with the first layer as the innermost layer comprising at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1, the second layer as an adhesive layer comprising non-crystalline polyolefin, adhesive polyolefin or an ethylene-vinyl acetate copolymer, and the third layer consisting of an ethylene-vinyl alcohol copolymer. The third layer functions as a barrier for preventing the contaminant from migrating from outside the third layer toward the first layer as the innermost layer.

FIG. 4



EP 0 698 487 A1

Description

TECHNICAL FIELD

5 The present invention relates to contamination preventing sealant films, and more particularly to a contamination preventing sealant film which is useful as a material for forming the innermost layer of films for medical containers, medical container packaging films and medical container covering films.

BACKGROUND ART

10 From the viewpoint of preventing deterioration of medicinals or breakage of containers and ensuring see-through properties, single-layer films or multi-layered films which are excellent in gas barrier properties, moisture impermeability, heat resistance, impact resistance and transparency have heretofore been used generally as plastic film materials, for example, for making medical containers, packaging medical containers or covering medical containers. These film materials include as a component a base film. Examples of resin material for the base film is, for example, nylon, polyethylene terephthalate, polyvinyl alcohol or the like.

Further in order to give improved heat-sealing properties, it has been practice to laminate a sealant film to the base film of the film material with a silicone, epoxy, urethane, urethane-epoxy, acryl or like adhesive. Chiefly used as the sealant film in this case is a film of resin having a low melting point and low density, such as low-density polyethylene. 20 Such a resin film affords a high heat-sealing strength, permits sealing at a low temperature, gives a specified heat-sealing strength despite adhesion of dust or the like, and is therefore excellent in quality and properties as a sealant film.

With the film material comprising the base film, adhesive layer and sealant film, the base film and the adhesive often contain contaminants.

These contaminants and causes for contamination are as follows.

- 25 (1) Various additives added to the material to be formed into the base film for giving improved properties to the film. Such additives are phthalic acid esters [(such as dioctyl phthalate (DOP), di-n-butyl phthalate (DNBP), diethyl phthalate (DEP), diethylhexyl phthalate (DEHP)], chlorinated paraffin, adipic acid esters, fatty acid amide, phosphorus derivatives antioxidants, phenol derivatives antioxidants, etc.
- 30 (2) It is likely that the extruder die will be coated with a rust inhibitor or release agent (such as silicone oil). The rust inhibitor or release agent adheres to and contaminates the base film when it is formed.
- (3) Contamination due to adhesion of the contaminant or contaminant-containing water to the outer surface of the base film.
- (4) In the case where the base film contains nylon resin, adipic acid or caprolactam as a component of the nylon resin.
- 35 (5) A reaction product present in the adhesive.

The sealant film providing the innermost layer of the film material conventionally available has no barrier properties to these contaminants, so that if the base film and/or the adhesive contains the contaminant, the contaminant migrates to the inside of the innermost layer through the adhesive layer and the sealant film.

40 Accordingly, the products prepared from the film material, such as medical containers, medical container packaging bags or medical container covers, are unable to protect the contents, such as medicinals, from contamination with contaminants.

Further if the medicinal is contaminated with contaminants, decomposition of the medicinal, a change in its appearance, deterioration or like problem is likely to arise.

45 DISCLOSURE OF THE INVENTION

An object of the present invention is to provide a contamination preventing sealant film having excellent heat-sealing properties and barrier properties to the foregoing contaminants.

50 Another object of the invention is to provide contamination preventing film for medical containers, medical container packaging film and medical container covering film which include the sealant film as the innermost layer.

Still another object of the invention is to provide contamination preventing products, such as a medical container, a medical container packaging bag (hereinafter referred to as a "packaging bag") and a medical container cover (hereinafter referred to as a "cover"), which include the sealant film as the innermost layer.

55 Other features of the present invention will be clarified by the following description.

The present invention provides a contamination preventing sealant film which is a multilayer sealant film having as the innermost layer a first layer comprising at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1, the sealant film being characterized in that a third layer comprising an ethylene-vinyl alcohol copolymer is laminated to the outer side of the first layer with a second

layer serving as an adhesive layer and comprising an amorphous polyolefin, adherent polyolefin or ethylene-vinyl acetate copolymer.

The contamination preventing sealant film of the present invention may comprise, in addition to the three-layer structure of the first to third layers, a fourth layer and a fifth layer successively formed over the outer side of the third layer constituting the outermost layer of the structure.

In this case, the resin mentioned for the second layer is used for forming the fourth layer, and the resin mentioned for the first layer is used for forming the fifth layer.

The sealant film of the present invention is usable for forming the innermost layer of films for medical containers, medical container packaging films and medical container covering films.

The term "films for medical containers" as used herein refers to films for use in forming medical containers.

The term "medical container packaging films" refers to films for forming packaging bags which wraps and seals off a medical container entirely (hereinafter referred to as "packaging films").

The term "medical container covering films" refers to films for forming a cover which wraps in at least one compartment of a medical container locally adheres to the container (hereinafter referred to as "covering films").

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a sectional view showing a contamination preventing sealant film of the three-layer type according to the invention.

FIG. 2 is a sectional view showing a contamination preventing sealant film of the five-layer type according to the invention.

FIG. 3 is a view in vertical section showing an example of medical container formed from a film including a contamination preventing sealant film of the invention.

FIG. 4 is a view in vertical section showing an example of packaging bag prepared from a like film.

FIG. 5 is a view in vertical section showing another example prepared from the same film.

FIG. 6 is a view in vertical section showing an example of cover prepared from a like film.

FIG. 7 is a view in vertical section showing the contamination preventing sealant film of the invention as locally adhered to the base film of a packaging film or covering film.

BEST MODE OF CARRYING OUT THE INVENTION

Embodiments of the present invention will be described below with reference to the accompanying drawings.

FIG. 1 shows an example of contamination preventing sealant film having a three-layer structure and embodying the present invention.

A first layer 1 providing the innermost layer has desirable heat-sealing properties and is made from at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1. Among these, linear low-density polyethylene or low-density polyethylene is preferable.

The first layer 1 may comprise a mixture of at least two resins which are different in miscibility.

To be suitable, the low density mentioned above is a density of about 0.905 to about 0.945 g/cm³.

The thickness of the first layer 1 is at least 10 μ m, and is suitably determined preferably from the range of about 10 to about 40 μ m.

To prevent contaminants from migrating from outside toward the innermost layer (first layer), a third layer 3 having barrier properties to contaminants is formed over the outer side of the first layer 1 with a second layer 2 interposed therebetween.

The third layer 3 is made from an ethylene-vinyl alcohol copolymer (also termed saponified ethylene-vinyl acetate copolymer) having barrier properties to contaminants. It is suitable that the thickness of this layer be at least 10 μ m, preferably about 10 to about 25 μ m. The ethylene copolymerization mole ratio of the resin can be selected from a wide range, and is preferably 29 to 44% in view of flexibility, barrier properties to contaminants, etc.

Although the ethylene-vinyl alcohol copolymer for forming the third layer 3 can be made into a two-layer film along with the first layer 1 by co-extrusion, this method is not desirable since the resulting film is much inferior to usual co-extruded films in interlaminar strength. According to the invention, therefore, the second layer 2 which is highly adherent to the third layer 3 and the first layer 1 (innermost layer) is provided between the two layers.

The second layer 2 comprises an amorphous polyolefin, adherent polyolefin, or ethylene-vinyl acetate copolymer which is improved in adhesion when required, and is preferably 5 to 25 μ m, more preferably 5 to 15 μ m, in thickness.

The amorphous polyolefin to be used for forming the second layer 2 is, for example, an ethylene- α -olefin copolymer (hereinafter referred to as an "amorphous polyethylene") having a density of 0.880 to 0.890 g/cm³, propylene- α -olefin copolymer (hereinafter referred to as an "amorphous polypropylene") having a density of 0.880 to 0.890 g/cm³, or the like. Among these, the amorphous polyethylene is desirable. Examples of the α -olefins are, for example propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene

and the like which have 3 to 12 carbon atoms. Among these, 1-butene is desirable for forming the copolymer. However, propylene is excluded in the case of propylene- α -olefin copolymer.

The adherent polyolefin is prepared by graft-polymerizing maleic acid with polyethylene, polypropylene or like polyolefin and improved in adhesion. Examples of such polyolefins are adherent polyethylene, adherent polypropylene, etc., among which adherent polyethylene is preferred.

The ethylene-vinyl acetate copolymer exhibits good adhesion or poor adhesion depending on the ethylene copolymerization mole ratio of the resin. The copolymer is used as it is in the former case, whereas in the latter case, maleic acid is graft-polymerized with the copolymer to impart improved adhesion.

The first layer 1 and the second layer 2 are formed inwardly of the third layer 3 having barrier properties to contaminants and are therefore undesirable if containing contaminants. Accordingly, the foregoing resins for forming the first layer 1 and the second layer 2 are used without adding thereto additives which will become contaminants.

The third layer 3 is formed also without using any additive, so that no additive migrates from the third layer 3 inward.

It is required that the contamination preventing sealant film of the present invention at least have a three-layer structure comprising the first layer 1 (innermost layer), second layer 2 and third layer 3 as shown in FIG. 1. Another layer can be laminated to the outer side of the third layer 3 when so required.

A suitable known plastic resin layer can be selected for use as the other layer in this case. Presence of a contaminant in this layer poses no particular problem.

To retain transparency and flexibility of the sealant film of the invention, it is desired to laminate as the other layer a fifth layer 5 which comprises at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1 using a fourth layer 4 serving as an adhesive layer and comprising an amorphous polyolefin, adherent polyolefin, or ethylene-vinyl acetate copolymer which is improved in adhesion when required, as seen in FIG. 2. The thickness of the fourth layer 4 is suitably selected from the range preferably of 5 to 25 μm , more preferably of 5 to 15 μm . The thickness of the fifth layer 5 is suitably selected from the range preferably of 10 to 40 μm , more preferably of 10 to 20 μm .

The overall thickness of the contamination preventing sealant film of the type shown in FIG. 1, as well as of the type shown in FIG. 2, is suitably selected from the range of 50 to 80 μm .

The multilayer sealant film of the present invention is produced by water-cooled or air-cooled co-extrusion inflation, T-die co-extrusion or like process.

A film for medical containers, packaging film or covering film is obtained by laminating a base film to the outer layer of the present sealant film.

The sealant film of the invention can be laminated to the base film by dry lamination or wet lamination. Further in the case where the outermost layer of the present sealant film has heat-sealing properties, and the innermost layer of the base film has heat-sealing properties, heat-sealing means may be used for adhering the films.

When the above-mentioned films are formed into suitable shapes in the usual manner, various products are available which include medical containers, packaging bags and covers like the examples shown in FIGS. 3 to 6.

FIG. 3 shows a medical container film prepared by laminating a sealant film A of the invention to a base film B, and a medical container is formed from the film. Various known films for use in making medical containers are usable as the base film B.

FIGS. 4 and 5 show a packaging film with the invention sealant film A laminated to the base film B₁ and packaging bags b formed from the film. Medical containers a₁, a₂ are enclosed in the respective bags b. FIG. 5 shows a double-chamber container a₂ as enclosed in a folded state.

In the case where the medicinals within the medical containers a₁ and a₂ are very susceptible to degradation due to oxygen and moisture, the base film B₁ to be used for forming the packaging bags b needs to be film having gas barrier properties and moisture impermeability to preclude the degradation of the medicinals in the containers a₁ and a₂.

Usable as the base film B₁ having high gas barrier properties and moisture impermeability is a composite film comprising a polyolefin film and aluminum foil laminated thereto and impervious to oxygen and water vapor, a single or multi-layered resin film material comprising polyethylene terephthalate (PET), polyvinylidene chloride, polyvinyl alcohol, polyamide, ethylene-vinyl acetate copolymer as saponified or the like, or a laminated film material of the resin film and the above composite film.

Other materials favorably usable include a composite film which comprises a polyvinyl alcohol film, polyethylene terephthalate film or saponified ethylene-vinyl acetate copolymer film, and a silicon oxide layer formed on the film by vacuum deposition.

Given below are examples of multilayer films comprising such a composite film.

(1) A multilayer film comprising a composite film prepared by forming a silicon oxide layer on a polyvinyl alcohol film by vacuum deposition, and a PET film (outermost layer) formed on the silicon oxide layer of the composite film by dry lamination.

(II) A multilayer film which comprises a composite film prepared by forming a silicon oxide layer on a polyvinyl alcohol film by vacuum deposition, and the multilayer film (I) and which is prepared by dry lamination with the polyvinyl alcohol film of the film (I) superposed on the silicon oxide layer of the composite film.

The packaging bag b is used also for protecting the medical container a₁ or a₂ from an external impact. Used as the base film B₁ in this case is a single-layer or multilayer film material which includes as a component a film of PET, nylon, polyethylene, polypropylene or the like having a high impact strength.

FIG. 6 shows a covering film which comprises the sealant film A of the invention and a base film B₂ laminated thereto, and a cover c formed from the covering film and enclosing one chamber of the double-chamber container a₂ therewith.

The cover c is used for the same purpose as the packaging bag b, so that like the base films B₁, B₂ to be used is a film material having high gas barrier properties and moisture impermeability.

For use in the packaging film or the covering film, the sealant film A is adhered to the base film B₁ or B₂ over the entire surface thereof as seen in FIGS. 4 to 6, or locally thereto so as to provide a space between the base film B₁ or B₂ and the film A as shown in FIG. 7.

Although the contamination preventing sealant film, medical containers, packaging bags and cover embodying the invention are herein described with reference to FIGS. 1 to 7, the mode of practicing the invention as these embodiments, the shape or size thereof, etc. are in no way limited but the invention can of course be embodied variously without departing from the principle feature of the invention.

The present invention provides products made from a film material comprising the sealant film of the invention and a base film laminated to the outer layer thereof, i.e., medical containers, packaging bags and covers, such as those shown in FIGS. 3 to 6. The sealant film has barrier properties to contaminants and therefore eliminates the likelihood that the contaminants present in the base film and/or those from outside will penetrate into the medical container to prevent the contaminants from contaminating the medicinal.

The medical containers shown in FIGS. 3 to 6 are used for containing common medicinals, which may be powder preparations, liquid preparations or solid preparations.

Examples of powder preparations include antibiotics, anticancer agents, proteins, peptides, steroids, fibrinolytic agents and vitamins. Examples of antibiotics are cephalosporins, β -lactam type such as ampicillin, carbapenem type such as imipenem, aminoglycoside type such as kanamycin, polypeptide type such as vancomycin and macrolide type such as erythromycin. Examples of liquid preparations are physiological saline, glucose solution, distilled water for injection, electrolytic solutions, amino acid solutions, fat emulsions, etc.

Incidentally, the powder preparations such as antibiotics among the above-mentioned medicinals are necessary to be dissolved in the physiological saline or the glucose solution for injection into a patient when being used. Therefore, there has been recently developed a multi-compartment container having two compartments as shown in Figs 6 in order to render their operations simple.

Figs. 6 shows multi-compartment container. The upper compartment thereof accommodates an antibiotic easy to be adversely affected by even a little amount of contaminants, and the lower compartment accommodates a solvent such as physiological saline or glucose solution. Only the upper compartment is double-covered with the cover.

Embodiments of the invention and comparative examples will be described below, followed by a test example wherein they were used.

Embodiment 1 (FIG. 1 type)

Using a water-cooled co-extrusion inflation machine, a sealant film was prepared which had a three-layer structure comprising an outer layer, i.e., a 15- μ m-thick third layer of ethylene-vinyl alcohol copolymer (product of Kuraray Co., Ltd. 44% in ethylene copolymerization mole ratio, hereinafter referred to as "EVOH (1)"), an intermediate layer, i.e., a 15- μ m-thick second layer of amorphous polyethylene (product of Mitsui petrochemical Industries, Ltd., brand name: TAFMER

A, 0.885 g/cm³ in density, hereinafter referred to as "PE (1)"), and the innermost layer, i.e., 20- μ m-thick first layer of linear low-density polyethylene (product of Mitsui Petrochemical Industries, Ltd., 0.940 g/cm³ in density hereinafter referred to as "L-LDPE (1)").

In the same manner as Embodiment 1, sealant films of Embodiments 2 to 7 and Comparative Example 1 were prepared.

Embodiment 2 (FIG. 1 type)

Third layer (outer layer): EVOH (1), 15 μ m in thickness

Second layer (intermediate layer): ethylene-vinyl acetate copolymer (product of Mitsui Petrochemical Industries, Ltd., vinyl acetate (VA): 6 wt. %, hereinafter referred to as "EVA (1)"), 15 μ m in thickness

First layer (innermost layer) : linear low-density polyethylene (product of Mitsui Petrochemical Industries, Ltd., 0.923 g/cm³ in density, hereinafter referred to as "L-LDPE (2)"), 20 µm in thickness

Embodiment 3 (FIG. 2 type)

Outer layer (fifth layer): L-LDPE (1), 15 µm in thickness

Fourth layer: adherent polyethylene (product of Mitsui Petrochemical Industries, Ltd., brand name: ADMER, hereinafter referred to as "PE (2)"), 5 µm in thickness

Third layer: ethylene-vinyl alcohol copolymer (product of Kuraray Co., Ltd., 29% in ethylene copolymerization mole ratio, hereinafter referred to as "EVOH (2)"), 15 µm in thickness

Second layer: PE (2), 5 µm in thickness

Innermost layer (first layer): L-LDPE (1), 15 µm in thickness

Embodiment 4 (FIG. 2 type)

Outer layer (fifth layer): L-LDPE (1), 10 µm in thickness

Fourth layer: PE (1), 10 µm in thickness

Third layer: EVOH (2), 10 µm in thickness

Second layer: PE (1), 10 µm in thickness

Innermost layer (first layer): L-LDPE (1), 10 µm in thickness

Embodiment 5 (FIG. 2 type)

Outer layer (fifth layer): L-LDPE (1), 10 µm in thickness

Fourth layer: PE (2), 10 µm in thickness

Third layer: EVOH (2), 25 µm in thickness

Second layer: PE (2), 10 µm in thickness

Innermost layer (first layer): L-LDPE (1), 10 µm in thickness

Embodiment 6 (FIG. 2 type)

Outer layer (fifth layer): L-LDPE (1), 10 µm in thickness

Fourth layer: PE (2), 5 µm in thickness

Third layer: EVOH (2), 25 µm in thickness

Second layer: PE (2), 5 µm in thickness

Innermost layer (first layer): L-LDPE (1), 10 µm in thickness

Embodiment 7 (FIG. 1 type)

Third layer (outer layer): EVOH (1), 10 µm in thickness

Second layer (intermediate layer): PE (2), 10 µm in thickness

First layer (innermost layer): L-LDPE (1), 30 µm in thickness

Comparative Example 1

Single layer (sealant film): L-LDPE (1), 50 µm in thickness

The films of Embodiments 1 to 7 and Comparative Example 1 were prepared by water-cooled co-extrusion inflation with a flat width of 240 mm. The film take-off speed for Embodiments 1, 2 and 7, and Comparative Example 1 was 8 to 10 m/min, and the film take-off speed for Embodiments 3 to 6 was 9 to 13 m/min.

Experimental Example

The base film X stated blow was united to the sealant films of Embodiments 1 - 7 over the outer layer thereof by dry lamination to obtain films as Embodiments IX - 7X.

The base film Y given below was united to the sealant films of Embodiment 1 and Comparative Example 1 over the outer layer thereof to obtain films as Embodiment 1Y and Comparative Example 1Y. (The dry lamination process was used for Embodiment 1, and heat-sealing means for Comparative Example 1.)

The base film Z given below was laminated to the sealant film of Comparative Example 1 by heatsealing means to obtain a film as Comparative Example 1Z

X. L-LDPE (1), 300 μm in thickness

Y. Oriented nylon (ONy), 15 μm /urethane-epoxy resin (adhesive)/low-density polyethylene (LDPE), 40 μm in thickness

Z. Polyethylene terephthalate (PET), 12 μm /urethane-epoxy resin (adhesive)/(LDPE), 50 μm in thickness

When the sealant film of the invention is laminated to the base films X and Y, the film surfaces to be united are treated by corona discharge first and then subjected to the usual dry lamination process.

The oriented nylon (ONy) film, polyethylene terephthalate (PET) film and low-density polyethylene (LDPE) film for constituting the base films, and the urethane-epoxy resin (adhesive) for use in dry lamination were all those generally available commercially.

The films of Embodiments IX - 7X, Embodiment IV, Comparative Example IV and Comparative Example IZ were used for making medical containers wherein the sealant film served as the innermost layer, and the containers were tested by the following contamination experiments.

Contamination Experiment 1: DOP, di-n-butyl phthalate (DNBP) and diethyl phthalate (DEP) used as contaminants were applied by coating or spraying to the outer surface cm) which was filled with 1 g (potency) of cephalosporin sodium (CEZ), and thereafter preserved at 40 °C and 75% RH (relative humidity) for 3 months. The CEZ filled in was checked for the migration of the contaminants by GLC (Gas Liquid Chromatography) and the GC-MS (Gas Liquid chromatography-Mass Spectrography) method.

Contamination Experiment 2: After a die rust inhibitor (KG type, product of Kobe Gosei Co., Ltd.) was sprayed onto the outer surface of the medical container as filled with 1 g (potency) of CEZ, it was preserved under the condition of 40°C in temperature and 75 % in RH for two weeks. Then, it was checked whether contaminants were migrated into the filled CEZ by GLC and the GC-MS method Contaminant Extraction Method and Extract Analysis Method:

Special-grade n-hexane (product of Wako Junyaku Co., Ltd.) was purified by distillation to remove the influence of DOP or DNBP present in the reagent. The CEZ contained was first fully dissolved in 10 to 20 ml of purified ultrapure water (product of Millipore limited, brand name: MILLIQ), and the solution was placed into a separating funnel washed with a sufficient amount of purified ultrapure water. After purified ultrapure water was further added to the solution to a combined amount of 150 ml, 150 ml of the purified n-hexane was further added. The contaminants were allowed to fully migrate into the n-hexane fraction. The n-hexane fraction was concentrated to 10 ml, and a portion thereof was subjected to GLC analysis under the conditions given below.

The remaining n-hexane fraction was concentrated again to dryness, resulting solid was dissolved again in 0.2 ml of n-hexane as purified by distillation, and the solution was subjected to the GC-MS method to be described below.

Tables 1 and 2 show the results of these analyses.

The sealant film used for comparative examples, i.e., the single-layer film of L-LDPE (1), was checked for contamination by cutting out a piece approximately 1 cm square from the film, subjecting 2 g of the piece to extraction with 150 ml of n-hexane as purified by distillation, concentrating the extract to dryness and dissolving again the dry solid in the n-hexane purified by distillation and analyzing it by GLC and the GC-MS method, whereby the film was found totally free from any contaminants.

(Devices Used)

Products of Hewlett-Packard Co.

HP5890 Series II gas chromatograph

HP3396 Series II integrator

HP7673 Controller

(Analysis Conditions)

The conditions for gas chromatographic analysis were as follows.

Column: Ultra Alloy (HT) 30 m x 0.25 mm ID x 0.25 μm

Column temp.: 60°C → 10°C/min temp. rise → 300°C

Column flow rate: 1.30 ml/min

Carrier gas: He 4.0 kg/cm²

Inlet temp.: 200°C

Detector: FID

Detector temp.: 310°C

Sensitivity: RANGE=0 ATT=0

Injection method: Splitless high-pressure injection

Inlet pressure: 30 psi (0 min) - 99 psi/min - 20 psi (constant flow)

Split ratio: 38:1

Amount injected: 1 μ l of solution

(Measuring Conditions) GC-MS

Device: HP-5890/5971A-GC-MS (product of Hewlett-Packard Co., LTD.)

Column: J & W DB-1 x 30 m x 0.25 mm x 0.25 μ m

Column temp.: 100°C - 10°C/min - 280°C

Inlet temp.: 280°C

Detector temp.: 280°C

Detector: MSD

Amount injected: 2 μ l, splitless

*Table 1

*Table 2

CAP: Caprolactam, EPO: epoxy compound

Rust inhibitor components: The peak obtained by analyzing the inhibitor alone is compared with the retention time of fragment data. Meanings of the symbols in Tables 1 and 2:

- : The contaminants were not recognized.

○ : The analysis gave a peak having the same retention time as an authentic substance corresponding to the contaminant, or data of the same fragment as the authentic substance corresponding to the contaminant.

The present invention provides sealant films having excellent properties to prevent contamination while retaining satisfactory heat-sealing properties. Use of films including the sealant film affords medical containers, packaging bags and covers which effectively prevent contamination.

Table 1

Result of Contamination Experiment 1						
		DOP	DNBP	DEP	CAP	EPO
Embodiment 1X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 2X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 3X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 4X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 5X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 6X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 7X	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Embodiment 1Y	GLC	-	-	-	-	-
	GC-MS	-	-	-	-	-
Comp.Ex. 1Y	GLC	○	○	○	○	○
	GC-MS	○	○	○	○	○
Comp.Ex. 1Z	GLC	○	○	○	-	○
	GC-MS	○	○	○	-	○

Table 2

Result of Contamination Experiment 2				
		RUST INHIBITOR	CAP	EPO
Embodiment 1X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 2X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 3X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 4X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 5X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 6X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 7X	GLC	-	-	-
	GC-MS	-	-	-
Embodiment 1Y	GLC	-	-	-
	GC-MS	-	-	-
Comp.Ex. 1Y	GLC	○	○	○
	GC-MS	○	○	○
Comp.Ex. 1Z	GLC	○	-	○
	GC-MS	○	-	○

Claims

1. A contamination preventing sealant film which is a multilayer sealant film having as the innermost layer a first layer comprising at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1, the sealant film being characterized in that a third layer comprising an ethylene-vinyl alcohol copolymer is laminated to the outer side of the first layer with a second layer serving as an adhesive layer and comprising an amorphous polyolefin, adherent polyolefin or ethylene-vinyl acetate copolymer.
2. A contamination preventing sealant film as defined in claim 1 wherein the first layer comprises linear low-density polyethylene or low-density polyethylene, and the second layer comprises an amorphous polyethylene, adherent polyethylene or ethylene-vinyl acetate copolymer.
3. A contamination preventing sealant film as defined in claim 1 or 2 wherein the first layer has a thickness of 10 to 40 μm , the second layer has a thickness of 5 to 25 μm , and the third layer has a thickness of 10 to 25 μm .
4. A contamination preventing sealant film as defined in any one of claims 1 to 3 which is characterized in that a fifth layer comprising at least one resin selected from the group consisting of linear low-density polyethylene, low-density polyethylene, polypropylene and polybutene-1 is laminated to the outer side of the third layer with a fourth layer serving as an adhesive layer and comprising an amorphous polyolefin, adherent polyolefin or ethylene-vinyl acetate copolymer.

5. A contamination preventing sealant film as defined in claim 4 wherein the fourth layer comprises an amorphous polyethylene, adherent polyethylene or ethylene-vinyl acetate copolymer, and the fifth layer comprises linear low-density polyethylene or low-density polyethylene.
- 5 6. A contamination preventing sealant film as defined in claim 4 or 5 wherein the fourth layer has a thickness of 5 to 25 μm , and the fifth layer has a thickness of 10 to 40 μm .
7. A contamination preventing sealant film as defined in any one of claims 1 to 6 wherein the film is 50 to 80 μm in overall thickness.
- 10 8. A film for medical containers which comprises as the innermost layer of a film for a medical container a contamination preventing sealant film defined in any one of claims 1 to 7.
- 15 9. A film for packaging medical containers which comprises as the innermost layer of a film for packaging a contamination preventing sealant film defined in any one of claims 1 to 7.
10. A film for covering medical containers which comprises as the innermost layer of a film for a cover a contamination preventing sealant film as defined in any one of claims 1 to 7.
- 20 11. A product formed from a film as defined in claim 8, 9 or 10.

25

30

35

40

45

50

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6





FIG. 7



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP95/00410

A. CLASSIFICATION OF SUBJECT MATTER

Int. Cl⁶ B32B27/28, B32B27/08, A61J1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int. Cl⁶ B32B27/28, B32B27/08, A61J1/00

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho 1926 - 1995

Kokai Jitsuyo Shinan Koho 1971 - 1995

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP, 4-147853, A (Toppan Printing Co., Ltd.), May 21, 1992 (21. 05. 92) (Family: none) Claim, lines 10 to 13, lower left column, page 2	1
Y	Claim, table 1	3
	JP, 62-234930, A (W.R. Grace & Co.), October 15, 1987 (15. 10. 87) & EP, 236099, A & US, 4746562, A & US, 4753700, A & US, 4755419, A & US, 5004647, A	
X	Claim	4, 5
Y	Claim, line 2, upper left column to line 6, upper right column, page 4	6, 7

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"B" earlier document her published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" documents referring to oral disclosures, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later documents published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

June 1, 1995 (01. 06. 95)

Date of mailing of the international search report

June 20, 1995 (20. 06. 95)

Name and mailing address of the ISA/

Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)